



EW2068

WOVEN

GLOBAL
SOLUTION
PROVIDER



 ca. 70 g/m²

 150 cm

 100% PES



Oeko-Tex: Product class 2



(1010) white










(1095) black

CARE RECOMMENDATION



GINETEX code: G X X B E Z Z

FUSING RECOMMENDATION

			
	130-150 °C	12-15 sec	2 - 4 bar 20 - 40 N/cm ²
	130-150 °C	12-15 sec	350 - 500 p/cm ²
			
	Continuous press		 Flat press

NOTE:

Kufner recommends testing prior to industrial use. All order is subject to our General Terms and Conditions.