

 ca. 30 g/m²

 150 cm


% 50%PES 50%PA

 Oeko-Tex: Product class 2
Tested for harmful substances according to Oeko-Tex® Standard 100











- (1010) white
- (1260) medium grey melange

CARE RECOMMENDATION



GINETEX code: D A A A E Z Z

FUSING RECOMMENDATION

			
	135-145 °C	15-18 sec	3 - 4 bar 30 - 40 N/cm ²
	135-145 °C	15-18 sec	500 - 1000 p/cm ²
	--		
	Continuous press		 Flat press

NOTE:
Kufner recommends testing prior to industrial use.
All order is subject to our General Terms and Conditions.