

ca. 25 g/m²

150 cm

% 50% PA 50% PES

CONFIDENCE IN TEXTILES
Tested for harmful substances according to Oeko-Tex® Standard 100
Oeko-Tex: Product class 2



- (1010) white
- (1260) medium grey melange

CARE RECOMMENDATION



GINETEX code: G X X B E Z Z

FUSING RECOMMENDATION

	130-150 °C	12-15 sec	2 - 4 bar 20 - 40 N/cm ²
	130-150 °C	12-15 sec	350 - 500 p/cm ²
	Continuous press		Flat press

NOTE:
Kufner recommends testing prior to industrial use.
All order is subject to our General Terms and Conditions.